

TEKNO 3TE

EN 854 3TE ISO 4079 3TE

RECOMMENDED FOR:
LOW AND MEDIUM PRESSURE, RETURN LINES

RACCOMANDATO PER:
LINEE DI BASSA E MEDIA PRESSIONE, LINEE DI RITORNO



Code	Hose size			Outside diameter		Max working pressure		Min burst pressure		Min bend radius		Weight		
	D.N.	Inch	mm	Inch	mm	PSI	Bar	PSI	Bar	Inch	mm	Lb/ft	kg/mt	
TH3TE03	5	3/16"	4,8	0,504	12,80	2320	160	9280	640	1,574	40	0,09	0,14	
TH3TE04	6	1/4"	6,4	0,566	14,40	2103	145	8410	580	1,770	45	0,11	0,17	
TH3TE05	8	5/16"	7,9	0,665	16,90	1885	130	7540	520	2,164	55	0,14	0,22	
TH3TE06	10	3/8"	9,5	0,728	18,50	1595	110	6380	440	2,754	70	0,16	0,25	
TH3TE08	12	1/2"	12,8	0,854	21,70	1349	93	5394	372	3,344	85	0,20	0,31	
TH3TE10	16	5/8"	16,0	1,019	25,90	1160	80	4640	320	4,131	105	0,28	0,41	
TH3TE12	19	3/4"	19,0	1,141	29,00	1015	70	4060	280	5,114	130	0,31	0,47	
TH3TE16	25	1"	25,4	1,412	35,90	798	55	3190	220	5,901	150	0,42	0,63	
TH3TE20	31	1" 1/4	31,8	1,664	42,30	653	45	2610	180	7,474	190	0,51	0,76	

**TEKNO 3TE****3/8"**

(9,5mm)

EN 854 3TE
ISO 4079 3TE110 Bar
11 MPa**1595 Psi**

MARKING/MARCATURA: TRANSFER TAPE

OPERATING**TEMPERATURE RANGE:**

-40°C/+100°C
(-40°F to +212°F)

TUBE:

oil resistant synthetic rubber

REINFORCEMENT:

2 high tensile textile braids

COVER:

weather resistant synthetic rubber

**TEMPERATURA
DI ESERCIZIO:**

-40°C/+100°C
(-40°F to +212°F)

SOTTOSTRATO:

gomma sintetica resistente agli oli

RINFORZO:

2 trecce tessili ad alto carico

COPERTURA:

gomma sintetica resistente agli agenti atmosferici.